

ANTI CORROSION PRIMER is an Epoxy based primer with exceptional adhesion properties to aluminium, galvanised steel, stainless steel and mild steel. Excellent corrosive properties with 400 hours salt spray resistance. Ideal for applications where there is a mixture of metal substrates and fast re-coat times are needed.

Features and benefits

- Direct adhesion onto aluminium, galvanise, stainless and mild steel.
- Excellent anti-corrosive properties
- Very good overcoat times
- Available in 2 colours

Suitable substrates

- Aluminium
- Galvanised Steel
- Stainless Steel
- Mild Steel

Physical and chemical data

Basis of binder	Epoxy
Colour	Red Oxide / Grey Oxide
Coverage	1.5 - 2.0m ²
Temperature resistance	Up to 110°C
Storage stability	10 years if appropriate storage provided - 10°-25°C, humidity max. 60%)
Size	500ml aerosol
VOC content	638g/lt
Drying times	
Touch dry	10 - 20 mins
Dry to handle	30 mins

Environmentally sound

The products supplied by ProXL are 100% free of heavy metals and the caps and packaging are made of recyclable material.

Disposal

Completely emptied cans should be put in recycling skips or appropriate container. Cans which are not empty should be disposed off as special refuse.

This application and technical information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively is the responsibility of the user.

Application guide

- Surface must be clean, dry and dust free.
- Abrade the surface
- Shake aerosol for at least two minute after the agitator ball is free.
- Shake aerosol during use
- Apply at a distance of 25 - 30 cm from the treatment area
- Apply several coats allowing for a 5 - 10 mins flash off between coats
- For additional protection follow with a suitable topcoat like ProXL Industrial RAL colours.
- After use turn aerosol upside down and empty valve for 2 - 3 seconds

