

PROXL Generation20 Universal Hardener has been developed for achieving superior results when used at a 2 :1 mix ratio with 2K Acrylic Solid Colours and 2K Clearcoats. It is available in three speeds to cater for all types of repair and drying conditions.

Features and benefits

- High isocyanate content for long term durability
- Suitable for use with most 2K paint systems
- Available in three curing speeds

Drying times @ 20°C:

Mixed 2:1	U2KHG20-ST Standard	U2KHG20-F Fast	U2KHG20-XF Extra Fast
Dust Dry	1 Hour	1 Hour	30 Minutes
Dry to touch	2.5 Hours	1.5 Hours	1.2 Hours
Dry	5 Hours	4 Hours	3 Hours

Recommended use at ambient temperatures:

	Full Respray	Panel Respray	Spot Repair
U2KHG20-ST STANDARD	10°C - 25°C	10°C - 30°C	20°C - 30°C
U2KHG20-F FAST	Not Recommended	10°C - 25°C	10°C - 30°C
U2KHG20-XF EXTRA FAST	Not Recommended	10°C - 25°C	10°C - 25°C

Technical Information

Isocyanate Hardener

Recommended mixing ratio: 2:1

Specific weight of 940 g/l

39% Solid Content

574 g/l VOC

Environmentally sound

The products supplied by ProXL are 100% free of heavy metals and the caps and packaging are made of recyclable material.

Disposal

Completely emptied cans should be put in recycling skips or appropriate container. Cans which are not empty should be disposed off as special refuse.

This application and technical information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively is the responsibility of the user.



DISCLAIMER OF LIABILITY

The information contained in this Technical Data Sheet is correct to the best of Alpha Coatings Limited trading as Capella Solutions Group's ("Capella") knowledge, however, you must satisfy yourselves that the Goods are suitable for your needs by way of your independent testing or other processes. Capella makes no warranty, representation, or guarantee regarding the information contained in the Technical Data Sheet or the suitability of its products and services for any particular purpose, nor does Capella assume liability arising out of the application or use of the Goods other than any liability which cannot be limited by law including but not limited to liability for: (a) death or personal injury caused by negligence; (b) fraud or fraudulent misrepresentation; and (c) breach of the terms implied by section 12 of the Sales of Goods Act 1979, in such circumstances Capella's total liability shall not exceed the cost of the Goods. Capella's total liability includes liability in contract, tort, negligence, breach of statutory duty, or otherwise. It is the Customer's responsibility to ensure that the guidance on the Technical Data Sheet is followed.