TECHNICAL DATA SHEET

PROPELLING EXCELLENCE

VHT TOPCOAT

Size 400ml Code: INDHTS400, INDHTC400, INDHTB400

VHT TOPCOAT give ultimate protection up to 800°c. Proves extremely sucessful for treated and untreated surfaces exposed to very high temperatures. It is suitable for use on flues and pipework. It can be sprayed onto bare metal without the need to prime first.

Features and benefits

- Heat resistant up to 800°c
- Good coverage and filling properties
- Excellent adhesion to steel, mild steel and aluminium
- Resistant to petrol, chemicals and weather

Suitable substrates

- Mild Steel
- Steel
- Aluminium

Environmentally sound

The products supplied by ProXL are 100% free of heavy metals and the caps and packaging are made of recyclable material.

Physical and chemical data

Basis of binder	Silicone resins
Colour	Various
Coverage	1.25 - 1.75m ²
Temperature resistance	Up to 800°c
Storage stability	10 years if appropriate storage provided - 10°-25°C, humidity max. 60%)
Size	400ml aerosol
VOC content	658g/lt
Drying times @ 20°c	
Touch Dry	5 - 10 minutes
Dry to Handle	10 - 15 minutes
Re-coat	After 30 - 60 minutes

Disposal

Completely emptied cans should be put in recycling skips or appropriate container. Cans which are not empty should be disposed off as special refuse.

This application and technical information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively is the responsibility of the user.

Application guide

- Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. Sand intact coatings to provide a proper key for adhesion.
- Do not apply any primer
- Shake aerosol for at least two minute after the agitator ball is free.
- Shake aerosol during use
- Apply at a distance of 25 cm from the treatment area
- Apply several thin coats allowing for a 5 10 mins flash off between coats
- Allow coating to dry at room temperature for 60 minutes. Then, heat for 30 - 60 minutes at 180°c to harden the paint layer.
- After use turn aerosol upside down and empty valve for 2 3 seconds



DISCLAIMER OF LIABILITY

The information contained in this Technical Data Sheet is correct to the best of Alpha Coatings Limited trading as Capella Solutions Group's ("Capella") knowledge, however, you must satisfy yourselves that the Goods are suitable for your needs by way of your independent testing or other processes. Capella makes no warranty, representation, or guarantee regarding the information contained in the Technical Data Sheet or the suitability of its products and services for any particular purpose, nor does Capella assume liability arising out of the application or use of the Goods other than any liability which cannot be limited by law including but not limited to liability for (a) breach of the terms implied by section 12 of the Sales of Goods Act 1979, in such circumstances Capella's total liability includes liability in contract, tort, negligence, breach of statutory duty, or otherwise. It is the Customer's responsibility to ensure that the guidance on the Technical Data Sheet is followed.