

ZINC RICH PRIMER provides a 90% zinc content coating with 1000 hours salt spray resistance. The product is intended for small areas or for touch-up of new, bare steel or galvanised steel in light industrial exposures, corrosive environments and high humidity areas.

Features and benefits

- Ultimate Cathodic protection of bare or galvanised steel
- 90% pure zinc content in dry film
- Re-coat within 30 mins
- 1000 hrs salt spray resistance
- Temperature resistant to 350oc
- Matches old zinc galvanising

Physical and chemical data

Basis of binder	Epoxy-Ester
Colour	Grey
Coverage	1.5 - 2m ²
Temperature resistance	Up to 350°C
Storage stability	10 years if appropriate storage provided - 10°-25°C, humidity max. 60%)
Size	500ml aerosol
VOC content	634g/lt
Drying times @ 20°C	
Touch Dry	10 - 15 minutes

Suitable substrates

- Galvanised Steel
- Mild Steel

Environmentally sound

The products supplied by ProXL are 100% free of heavy metals and the caps and packaging are made of recyclable material.

Disposal

Completely emptied cans should be put in recycling skips or appropriate container. Cans which are not empty should be disposed off as special refuse.

This application and technical information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively is the responsibility of the user.

Application guide

- Surface must be clean, dry and dust free
- Sand the surface slightly
- Shake aerosol for at least two minute after the agitator ball is free.
- Shake aerosol during use
- Apply at a distance of 25 cm from the treatment area
- Apply several coats allowing for a 5 - 10 mins flash off between coats
- Can be overcoated with a suitable topcoat like ProXL Industrial RAL colours.
- After use turn aerosol upside down and empty valve for 2 - 3 seconds



SYSTEM
Industrial

DISCLAIMER OF LIABILITY

The information contained in this Technical Data Sheet is correct to the best of Alpha Coatings Limited trading as Capella Solutions Group's ("Capella") knowledge, however, you must satisfy yourselves that the Goods are suitable for your needs by way of your independent testing or other processes. Capella makes no warranty, representation, or guarantee regarding the information contained in the Technical Data Sheet or the suitability of its products and services for any particular purpose, nor does Capella assume liability arising out of the application or use of the Goods other than any liability which cannot be limited by law including but not limited to liability for:(a) death or personal injury caused by negligence;(b) fraud or fraudulent misrepresentation; and (c) breach of the terms implied by section 12 of the Sales of Goods Act 1979, in such circumstances Capella's total liability shall not exceed the cost of the Goods. Capella's total liability includes liability in contract, tort, negligence, breach of statutory duty, or otherwise. It is the Customer's responsibility to ensure that the guidance on the Technical Data Sheet is followed.